

Miragrid[®] 2XT



Miragrid[®] 2XT biaxial geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Miragrid[®] 2XT biaxial geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas is accredited by [a2La](#) (The American Association for Laboratory Accreditation) and Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)). [NTPEP](#) test data.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D6637	lbs/ft (kN/m)	2000 (29.2)	2000 (29.2)
Creep Reduced Strength	ASTM D5262	lbs/ft (kN/m)	1266 (18.5)	
Long Term Allowable Design Load ¹	GRI GG-4(b)	lbs/ft (kN/m)	1096 (16.0)	

¹ NOTE: Allowable Long Term Strength values are for sand, silt and clay

Physical Properties	Unit	Typical Value
Mass/Unit Area (ASTM D5261)	oz/yd ² (g/m ²)	7.6 (258)
Roll Dimensions (width x length)	ft (m)	12 x 150 (3.6 x 46)
Roll Area	yd ² (m ²)	200 (165)
Estimated Roll Weight	lbs (kg)	101 (46)

© 2012 TenCate Geosynthetics Americas
Miragrid[®] is a registered trademark of Nicolon Corporation

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Creep Reduced Strength (ASTM D5262), and Long Term Allowable Design Load (GRI GG-4(b)) is not covered by our current A2LA accreditation.



PO Box 87380
Carol Stream, IL 60188
630.293.3111

www.roadfabrics.com

