



TruPave[®] Engineered Paving Mat

TruPave[®] Engineered Paving Mat is a wet-formed fiberglass/polyester hybrid paving mat comprised of randomly dispersed glass and polyester fibers, bonded together with a resinous binder system manufactured by Owens Corning. TruPave[®] Engineered Paving Mat conforms to ASTM D7239 Type I.

Mechanical Properties	Test Method	Unit	Roll Value		Asphalt Filled Tensile Strength ³
			Nominal	Max.	
Tensile Strength (MD)	ASTM D5035	lbf/2 in	80	--	> 180
Tensile Strength (CD)	ASTM D5035	lbf/2 in	70	--	> 180
Tensile Strength (bias angle) ¹	ASTM D5035 ²	lbf/2 in	70	-	> 180
Elongation @ max load	ASTM D5035	%	< 5	--	
Asphalt Retention	ASTM D6140	gal/yd ² (l/m ²)	0.18 (0.82)	--	
Melting Point	ASTM D276	F° (C°)	--	> 446 (> 230)	
Mass/Unit Area	ASTM D5261	oz/yd ² (g/m ²)	4.1 (136.6)	4.4 (146.3)	

¹ In paving applications, bias angle tensile strength can be a factor in mitigating multi-directional crack propagation

² Modified test sample is cut on a 45° angle and tested according to ASTM D5035

³ Asphalt filled test procedure per ASTM D6140 using PG 64-22 (Asphalt Retention Test Method)

All mat manufacturing procedures conform to International Organization for Standardization (ISO) 9002.

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2013 TenCate Geosynthetics Americas
TruPave[®] is a registered trademark of Owens Corning



PO Box 87380
Carol Stream, IL 60188
630.293.3111

www.roadfabrics.com

