



## Waterproofing Paving Mat Specification Sheet – GlasPave50

SPECIFICATIONS FOR USE IN ASPHALT OVERLAYS			
PROPERTY	TEST METHOD	GLASPAVE50	
		METRIC*	IMPERIAL**
TENSILE STRENGTH	ASTM D 5035	50 kN/m	280 lb/in.
ELONGATION AT BREAK	ASTM D 5035	≤ 5%	≤ 5%
MELTING POINT	ASTM D 276	> 232°C	> 450°F
MASS/UNIT AREA	ASTM D 5261	237 g/m <sup>2</sup>	7.0 oz/yd <sup>2</sup>
ASPHALT RETENTION	ASTM D 6140	.47 l/m <sup>2</sup>	.10 gal/yd <sup>2</sup>
ROLL LENGTH <sup>†</sup>		110 m	120 yds
ROLL WIDTH <sup>†</sup>		2 m	78.75 in.

<sup>†</sup> Product is sold by the roll. \*All metric values are nominal. \*\*All imperial values are approximate.

GlasPave™ is a trademark of Saint-Gobain Technical Fabrics (SGTF).

All statements herein are expressions of opinion, which we believe to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended. Values presented above are nominal and only to be used as guidelines.



**Tensor International Corporation**  
5883 Glenridge Drive, Suite 200  
Atlanta, Georgia 30328  
**800-TENSAR-1**  
[www.tensor-international.com](http://www.tensor-international.com)

GlasPave™ is a trademark of Saint-Gobain Technical Fabrics (SGTF). GlasPave™ is distributed in the United States of America, Canada and certain other countries by Tensar International Corporation (TIC). Inasmuch as SGTF and TIC have no control over installation design, installation workmanship, accessory materials, or conditions of application, SGTF and TIC do no warrant the performance or results of any installation or use of GlasPave™. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose.

©2009, Tensar International Corporation.

Exclusive distributors in the Americas for: 