

Mirafi[®] MPG⁴ (PGM-G⁴)

Mirafi[®] MPG⁴ (PGM-G⁴) is a 100% polypropylene filament nonwoven fabric, reinforced by mechanically bonded multi-axial network of reinforcing glass filaments. Mirafi[®] MPG⁴ (PGM-G⁴) was especially developed for the rehabilitation of asphalt roads.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

Mechanical Properties	Test Method	Unit	Average Roll Value
Tensile Strength @ 0°	ASTM D6637 Method A modified	lbs/in (kN/m)	459 (80)
Tensile Strength @ 90°			459 (80)
Tensile Strength @ 45°			459 (80)
Tensile Strength @ -45°			459 (80)
Tensile Elongation		%	< 3
Mass/Unit Area	ASTM D5261	oz/yd ² (g/m ²)	16.6 (563)
			Minimum Test Value
Melting Point ¹	ASTM D276	F° (C°)	Glass filaments are incombustible and temperature resistant up to 1472° (800°)
Asphalt Retention	ASTM D6140	gal/yd ² (l/m ²)	0.17 (0.8)
Glass by Weight		%	85

Physical Properties	Unit	Roll Characteristics	
Roll Dimensions (width x length)	ft (m)	6.25 x 300 (1.9 x 94.1)	12.5 x 150 (3.8 x 45.7)
Roll Area	yd ² (m ²)	208 (174)	
Estimated Roll Weight	lbs (kg)	228 (103)	

¹ Melting Point for Fiberglass



PO Box 87380
Carol Stream, IL 60188
630.293.3111

www.roadfabrics.com

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi[®] is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive
Pendergrass, GA 30567

Tel 706 693 2226
Tel 888 795 0808

Fax 706 693 4400
www.tencate.com

FGS000746
ETQR5

