


## PRODUCT IDENTIFICATION DATA SHEET

### H-Series™ FilterGrid™

### HX5.5™ Geogrid



Tensar HX5.5™ Geogrid  
Plan View

#### INTRODUCTION

H-Series™ FilterGrid™ is a composite geosynthetic consisting of H-Series geogrid bonded to a nonwoven geotextile. This product combines the advanced H-Series geogrid technology with the added functionality of a nonwoven geotextile where site conditions require additional filtration and/or separation.

#### GENERAL

1. The geogrid is manufactured from a polypropylene sheet, which is then punched and oriented. The resulting structure consists of continuous and non-continuous ribs forming three aperture geometries (hexagon, trapezoid, and triangle) and an unimpeded suspended hexagon.
2. The following properties are intended for product identification:

| Identification Properties <sup>1</sup>                       | General                              |
|--------------------------------------------------------------|--------------------------------------|
| Aperture Shape - A                                           | Hexagonal, Trapezoidal, & Triangular |
| Rib Shape - B                                                | Rectangular                          |
| Continuous Parallel Rib Pitch <sup>2</sup> - C, in (mm)      | 3.2 (80)                             |
| Rib Aspect Ratio <sup>3</sup> - D                            | > 1.0                                |
| Node Thickness <sup>2</sup> - E, in (mm)                     | 0.12 (3)                             |
| Color Identification                                         | Black                                |
| Product EPD Certification <sup>4</sup>                       | EN 15804 +A2:2019                    |
| Durability Properties                                        |                                      |
| Resistance to Chemical Degradation <sup>5</sup>              | 100%                                 |
| Resistance to Ultra-Violet Light and Weathering <sup>6</sup> | 90%                                  |

3. The needle punched nonwoven geotextile (nominal 6 oz/sy) is thermally bonded to the geogrid and is manufactured at a NTPEP audited facility. The geotextile shall have the following properties:

| Identification Properties for Geotextile | Test Method | English (MARV <sup>2</sup> ) | Metric (MARV <sup>2</sup> ) |
|------------------------------------------|-------------|------------------------------|-----------------------------|
| Grab Tensile Strength                    | ASTM D 4632 | 160 lbs.                     | 0.711 kN                    |
| Grab Elongation                          | ASTM D 4632 | 50%                          | 50%                         |
| Trapezoid Tear Strength                  | ASTM D 4533 | 60 lbs.                      | 0.267 kN                    |
| CBR Puncture Resistance                  | ASTM D 6241 | 410 lbs.                     | 1.823 kN                    |
| Permittivity                             | ASTM D 4491 | 1.5 sec <sup>-1</sup>        | 1.5 sec <sup>-1</sup>       |
| Water Flow                               | ASTM D 4491 | 110 gpm/ft <sup>2</sup>      | 4480 l/min/m <sup>2</sup>   |
| Apparent Opening Size (AOS)              | ASTM D 4751 | 70 Std. U.S.                 | 0.212 mm                    |
| UV Resistance                            | ASTM D 4355 | 70%/500 hrs                  | 70%/500 hrs.                |

#### NOTES

1. Unless indicated otherwise, values are minimum average roll values in accordance with ASTM D4759-02
2. Nominal dimensions
3. Ratio of the mid-rib height to the mid-rib width
4. Independently verified in accordance with ISO 14025:2006, ISO 14044:2006, and EN 15804:2019+A2.
5. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing
6. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355
7. Maximum Average Roll Value (MaxARV)


This product has been tested for quality control purposes in a GAI-LAP accredited laboratory and its EPD has been certified by UL Environment.



### PRODUCT IDENTIFICATION DATA SHEET

## H-Series™ FilterGrid™

## HX5.5™ Geogrid



Tensar HX5.5™ Geogrid  
Plan View

### DIMENSIONS AND DELIVERY

- The geogrid shall be delivered to the jobsite in roll form, each clearly labeled, as shown below:

| Property                                      | Standard Width Roll |         | Wide Width Roll |         |
|-----------------------------------------------|---------------------|---------|-----------------|---------|
| Roll Width <sup>2</sup> , ft (m)              | 12.5                | (3.8)   | 15.5            | (4.7)   |
| Roll Length <sup>2</sup> , ft (m)             | 164                 | (50)    | 164             | (50)    |
| Approx. Roll Area, SY (m <sup>2</sup> )       | 228                 | (191)   | 282             | (236)   |
| Approx. Roll Diameter <sup>7</sup> , In. (mm) | 18                  | (460)   | 18              | (460)   |
| Approx. Roll Weight <sup>7</sup> , Lbs. (Kgs) | 196                 | (89)    | 220             | (100)   |
| Approx. Rolls per Full-Truck                  | Min: 72             | Max: 80 | Min: 72         | Max: 80 |

### PERFORMANCE COMPARISON

The product properties shown above are intended for product identification, Quality Assurance (QA), and Quality Control (QC) purposes only. These properties are not used in any geogrid mechanical stabilization design methodologies or performance assessment and, as such, should not be evaluated or used in isolation. In order to compare the performance of different types of geogrids, performance validation data from full-scale trafficking testing must be used, as outlined in AASHTO R50-09 and other industry accepted geogrid mechanical stabilization design methodologies.

### NOTES

- Unless indicated otherwise, values are minimum average roll values in accordance with ASTM D4759-02
- Nominal dimensions
- Ratio of the mid-rib height to the mid-rib width
- Independently verified in accordance with ISO 14025:2006, ISO 14044:2006, and EN 15804:2019+A2.
- Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments in accordance with EPA 9090 immersion testing
- Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering in accordance with ASTM D4355
- Maximum Average Roll Value (MaxARV)

This product has been tested for quality control purposes in a GAI-LAP accredited laboratory and its EPD has been certified by UL Environment.



Tensar reserves the right to change its Product Identification Data Sheet at any time. It is the responsibility of the person specifying the use of this product and of the purchaser to ensure that Product Identification Data Sheet relied upon for procurement purposes are current and that the product is suitable for its intended use in each instance.

**Distributed By:**  
**Road Fabrics, Inc.**  
630-293-3111  
info@roadfabrics.com  
www.roadfabrics.com

This Product Data Identification Sheet (PIDS) supersedes any and all prior PIDS for the product designated above and is not applicable to any product shipped prior to March 1, 2021. Tensar and InterAx® are trademarks of Tensar or its affiliates in the US and many other countries. InterAx® geogrid and its method of manufacture and use are protected by U.S. Patent Nos. 11,390,015, 11,548,206, and 12,036,722. Patents or patent applications also exist in other countries. Final determination of the suitability of the above-mentioned information or product for the use contemplated, and its manner of use are the sole responsibility of the user. Tensar disclaims any and all express, implied, or statutory warranties, including but not limited to, any warranty of merchantability or fitness for a particular purpose regarding this product or other Tensar products, technologies, or services. The information contained herein does not constitute engineering advice (12/17/2024).