



MIRAFI S2000

MIRAFI® S2000 is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. MIRAFI S2000 is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MIRAFI® S2000 meets Build America, Buy America Act, Pub. L. No. 117-58, div. G §§ 70901-52.

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	450 (2003)	450 (2003)
Grab Tensile Elongation	ASTM D4632	%	50	50
Trapezoid Tear Strength	ASTM D4533	lbs (N)	175 (779)	260 (1157)
CBR Puncture Strength	ASTM D6241	lbs (N)	1310 (5830)	
Thickness	ASTM D5199	mils (mm)	180 (4.6)	
MAXIMUM OPENING SIZE				
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	100 (0.15)	
MINIMUM TEST VALUE				
UV Resistance (@ 500 hrs)	ASTM D4355	% strength retained	80	
PHYSICAL PROPERTIES		UNIT	MINIMUM AVERAGE ROLL VALUE	
Weight	ASTM D5261	oz/yd2 (g/m2)	20.0 (678)	
ROLL SIZE				
Roll Dimensions (width x length)		Ft (m)	15 x 500 (4.57 x 152.4)	
Roll Area		yd² (m²)	833 (696)	
Roll Weight		lb (kg)	1145 (519)	



Distributed By:
Road Fabrics, Inc.
630-293-3111
info@roadfabrics.com
www.roadfabrics.com

365 South Holland Drive Pendergrass, GA 30567

Tel +1 706 693 2226 www.tencategeo.us



Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.
FGS000763 ETQR10

