


PETROMAT MPM30



PETROMAT® MPM30 is constructed of high strength glass filaments bonded to a polyester fabric. PETROMAT MPM30 was especially developed for the rehabilitation of asphalt roads. TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE
Tensile Strength @ 0°	ASTM D5035 (2C-E)	lbs	200
Tensile Strength @ 90°	ASTM D5035 (2C-E)	lbs	200
Tensile Elongation	ASTM D5035	%	< 5
Mass/Unit Area	ASTM D5261	oz/yd ²	4.0

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM TEST VALUE
Melting Point	ASTM D276	F° (C°)	450° (232°)
Asphalt Retention	ASTM D6140	gal/yd ²	0.10

PHYSICAL PROPERTIES	UNIT	TYPICAL ROLL SIZE
Roll Dimensions (width x length)	ft	10 x 450 12.5 x 360
Roll Area	yd ²	500
Estimated Roll Weight	lbs	172



Distributed By:
Road Fabrics, Inc.
630-293-3111
info@roadfabrics.com
www.roadfabrics.com

365 South Holland Drive Pendergrass, GA 30567

Tel +1 706 693 2226 www.tencategeo.us



Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.
FGS000789 ETQR10

